

## **Tips When Using FlowCast**

### **How to Use FlowCast®**

In a clean, dry container; combine (by volume) 2 parts resin with 1 part hardener and mix thoroughly for 2 minutes. Then add desired pigments, continuing to mix until the epoxy is completely colored. After mixing, pour the epoxy into your mold. See our Knowledge Base for more detailed tutorials.

### **Repouring Between Coats**

Possible between 25 - 48 hours providing the previous pour is firm but still tacky. Once tack-free it is necessary to sand between layers to ensure proper adhesion

### **Recommended Storage**

55°F. through 85°F. with tightly sealed lids

### **Shelf Life**

Possible between 25 - 48 hours providing the previous pour is firm but still tacky. Once tack-free it is necessary to sand between layers to ensure proper adhesion